

Test Report No.: 68.431.22.0189.01

Dated: 2022-08-02



Applicant : YANGJIANG XINZUO INDUSTRY & TRADE CO.,LTD.
YUYUAN FIRST ROAD,DONGCHENG TOWN
INDUSTRIAL PARK,YANGDONG DISTRICT,YANGJIANG
CITY,GUANGDONG,CHINA

Sample Description : XINZUO PM8


Style No. / Name / Design No. : PM8-FHG SERIES

Country of Origin : China

Test Sample Receipt Date, Location : 2022-07-21, Shenzhen

Test Period, Location : From 2022-07-21 to 2022-07-29, Shenzhen

Test Result(s) : Refer to Section 3



Test Report No.: 68.431.22.0189.01

Dated: 2022-08-02



Purpose Of Examination / Conclusion:

No.	Test Item(s)	Conclusion
1	Leachable Lead Test for compliance with the selected requirement(s) in U.S. F.D.A. CPG 7117.05-Section 545.500 (for Silver-Plated Hollowware)	Pass
2.	Total Chromium Content	Report as is

Remarks:

- (1) The results relate only to the items tested.
- (2) Samples are tested as received.
- (3) The test item and samples were specified by the client
- (4) "Pass" means the measured result is within a limit, even when extended by expanded uncertainty. "Fail" means the measured result is beyond a limit, even when extended by expanded uncertainty. "Inconclusive" means the measured result can be within or beyond a limit when extended by expanded uncertainty. The confidence level of the expended uncertainty for "Pass", "Fail" and "Inconclusive" is 95%.

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
TüV Süd Group

Prepared by:

Reviewed by:



Simon Liu
Project Engineer

Angelina Wang
Supervisor

Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production. For further details, please see testing and certification regulation, chapter A-3.4.

1. Description of the Submitted Sample:

Sample Description	XINZUO PM8
	

2. List of Materials as identified by the Laboratory:

T. No.	Sample No.	Colour and Description	Photograph
T1	001	Silvery/ black stainless steel (Blade)	



3. Test Result

3.1 Leachable Lead

Test for compliance with the selected requirement(s) in U.S. F.D.A. CPG 7117.05-Section 545.500 (for Silver-Plated Hollowware)

Test Conditions:4% acetic acid at 22 ±2 °C for 24 Hours

Test Items	Unit	Results	MAXIMUM PERMISSIBLE LIMIT
		Sample 001	
Lead (Pb)-Trial 1	µg/ml	<0.10	Average of Lead (Pb) <7.0
Lead (Pb)-Trial 2	µg/ml	<0.10	
Lead (Pb)-Trial 3	µg/ml	<0.10	
Lead (Pb)-Trial 4	µg/ml	<0.10	
Lead (Pb)-Trial 5	µg/ml	<0.10	
Lead (Pb)-Trial 6	µg/ml	<0.10	
Average of Lead (Pb)	µg/ml	<0.10	
Conclusion		Pass	-

Note:

- "ug/ml" denotes microgram per milliliter.
- "<" denotes less than
- Specification is quoted from U.S. F.D.A. CPG 7117.05 - Section 545.500.

3.2 Total Chromium Content

Test Method: Digested by acid and analyzed by Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES)

Analyte	Results [%]
	Sample 001
Total Chromium(Cr)	13.57

Note:

- "%" denotes percentage by weight

-- END OF TEST REPORT--